ERAFLOR LVT CLICK Product Specifications

Category	Standard	EraFlor 3mm LVT Dryback
Materials Type	ISO 10582	Heterogeneous poly(vinyl chloride) flooring
Classification	ISO 10582	23、31
Technical feature	**Standard**	**EraFlor 3mm LVT Dryback**
Overall Thickness	ISO 10582	Standard value:2.90-3.13mm
Thickness of wear layer	ISO 10582	Standard value:0.27-0.33mm
(PUR)Surface treatment	-	High scratch resistance and stain resistance
Bevelled edges	-	Micro bevel
Technical performance	**Standard**	**EraFlor 3mm LVT Dryback**
Dimensional stability after exposure to heat	ISO 10582	≤0.10%
Squareness & Straightness	ISO 10582	≤0.15mm
Curling after exposure to heat	ISO 10582	≤1.0mm
Peel strength	ISO 10582	≥65N/50mm
Reaction to fire	EN 13501	Bfls1
Residual indentation	ISO 10582	≤0.10mm
Wear resistance	EN 660-2	Class T
Click system tensile strength	ISO 10582	/
Effect of a Castor chair	EN425	≥25000 revolutions
Slip resistance	DIN 51130	R9
Light fastness	EN ISO 105-B02	≥6
Resistance to chemicals	EN ISO 26987	Highest level (V)
Chemical performance	**Standard**	**EraFlor 3mm LVT Dryback**
Vinyl chloride monomer limit	GB18586	Not detected
VOC	GB18586	Not detected
Migration of certain elements	GB18586	Not detected